

TEST REPORT

REPORT NUMBER : TURT150137446
APPLICANT NAME **Gümrük ve Ticaret Bakanlığı (Ambarlı Gümrük Müdürlüğü)**
ADDRESS Marmara Mah. Limanlar Cad. No:49 Kat:2 Beylikdüzü / İstanbul
FAX NO : 0212 875 28 08
Attention : Mehmet Ali Kasırga
BUYER **NOT GIVEN**
IMPORTER: **Ceren Kağıt ve Kırtasiye San.A.Ş.**
SAMPLE DESCRIPTION : One sample of Color box with wooden brush
DATE IN : **25 August, 2015 (16:15)**
DATE OUT : **31 August, 2015**
MODEL NO : PLAY-SU001
NUMBER: 42591415/109
SUBJECT: 13.08.2015/15343100IM142332

TEST	Sample
PHTHALATE CONTENT	P
DETECTION OF AMINES DERIVED FROM AZOCOLOURANTS AND AZODYES	P
PRIMARY AROMATIC AMINES	P

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE/ LS : LACK OF SAMPLE

"This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>."

The test results relate only to the items tested. The whole and/or the part of this test report shall not be reproduced and shall not be shared with third parties, nor to be used for PR activities without the written permission of INTERTEK Test Hizmetleri A.S.

The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.

Melahat YILDIRIM
COORDINATOR

Sinan ÖNCEL / Customer Care Manager
Özlem CAVUMİRZA / Textile Laboratory Manager



Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No 23 Altındag Plaza Yenibosna-34197 / İSTANBUL
Phone : +90 212 496 46 46 Fax: +90 212 452 80 55
e-mail : intertekcg.turkiye@intertek.com
<http://www.intertek-turkey.com>



150137446

Test Method	Result	Requirements
PHTHALATE CONTENT		
INTERTEK IHTM AL.2.026 based on EN 14372 : 2004		
1-Composite sample of black dye, green dye, orange dye, pink dye		
		<u>RESULT (%, w/w)</u>
DIBUTYL PHTHALATE (DBP)	Not Detected	
DIETHYL HEXYL PHTHALATE (DEHP)	Not Detected	
BENZYL BUTYL PHTHALATE (BBP)	Not Detected	
SUM OF THREE PHTHALATES	Not Detected	
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)	
		<u>RESULT (%, w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	Not Detected	
DI-N-OCTYL PHTHALATE (DNOP)	Not Detected	
DI-ISO-DECYL PHTHALATE (DIDP)	Not Detected	
SUM OF THREE PHTHALATES	Not Detected	
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)	

REMARK = The Limit of 0.1% by weight was quoted according to Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content
 ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total Uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

PHTHALATE CONTENT

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

2-Composite sample of white dye, red dye, blue dye, yellow dye	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	Not Detected
DIETHYL HEXYL PHTHALATE (DEHP)	Not Detected
BENZYL BUTYL PHTHALATE (BBP)	Not Detected
SUM OF THREE PHTHALATES	Not Detected
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	Not Detected
DI-N-OCTYL PHTHALATE (DNOP)	Not Detected
DI-ISO-DECYL PHTHALATE (DIDP)	Not Detected
SUM OF THREE PHTHALATES	Not Detected
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK = The Limit of 0.1% by weight was quoted according to Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content
 ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total Uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

Detection of Amines Derived From Azocolourants and Azodyes

Test Method : BS EN 14362 - 1 : 2012 for Textile Material

Detection of Amines Derived From Azocolourants and Azodyes

- | | |
|--|---------|
| 1- Composite sample of black, green, orange water colours (without extraction) | <30 ppm |
| 2- Composite sample of red, white,pink water colours (without extraction) | |
| 3- Composite sample of blue, yellow water colours (without extraction) | |

<u>FORBIDDEN AMINE</u>	<u>CAS NO</u>	<u>1</u>	<u>2</u>	<u>3</u>
4-AMINOBIHENYL	92-67-1	N	N	N
BENZIDINE	92-87-5	N	N	N
CHLORO-O-4-CHLOR-O-TOLUIDINE	95-69-2	N	N	N
2-NAPHTHYLAMINE	91-59-8	N	N	N
*O-AMINOAZOTOLUENE	97-56-3	N	N	N
*2-AMINO-4-NITROTOLUENE	99-55-8	N	N	N
P-CHLOROANILINE	106-47-8	N	N	N
2,4-DIAMINOANISOLE	615-05-4	N	N	N
4,4'-DIAMINOBIHENYLMETHANE	101-77-9	N	N	N
3,3'-DICHLOROBENZIDINE	91-94-1	N	N	N
3,3'-DIMETHOXYBENZIDINE	119-90-4	N	N	N
3,3'-DIMETHYLBENZIDINE	119-93-7	N	N	N
3,3'-DIMETHYL-4,4'	838-88-0	N	N	N
DIAMINOBIHENYLMETHANE				
P-CRESIDINE	120-71-8	N	N	N
4,4'-METHYLENE-BIS-(2	101-14-4	N	N	N
CHLOROANILINE)				
4,4'-OXYDIANILINE	101-80-4	N	N	N
4,4'-THIODIANILINE	139-65-1	N	N	N
O-TOLUIDINE	95-53-4	N	N	N
2,4-TOLUYLENDIAMINE	95-80-7	N	N	N
2,4,5-TRIMETHYLANILINE	137-17-7	N	N	N
O-ANISIDINE	90-04-0	N	N	N
**P-AMINOAZOBENZENE	60-09-3	N	N	N
2,4 XYLIDINE	95-68-1	N	N	N
2,6 XYLIDINE	87-62-7	N	N	N

NOTE: *The amines o-amino-azotoluene and 2-amino-4-nitrotoluene are detected by its splitted product o-toluidine and 2,4- toluylenediamine.

**Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline and 1,4- phenylenediamine .

The presence of these colorants can not be reliably ascertained without additional information, e.g. chemical structure of the colorant used.

Remark:

1) ACCORDING TO THE OFFICIAL METHOD EN ISO/TS 17234:2003, IF 4-AMINODIPHENYL OR 2-NAPHTHYLAMINE OR 2,4-DIAMINOANISOLE IS FOUND EXCEEDING 30 PPM, THE USE OF FORBIDDEN AZO DYESTUFF CANNOT BE ASCERTAINED WITHOUT ADDITIONAL INFORMATION eg. THE CHEMICAL STRUCTURE OF THE DYESTUFF USED. TEXTILE OR POLYESTER METHOD CASES ONLY.

2) AZO COLORANTS CONTENT REQUIREMENT IN ANNEX XVII ITEM 43 OF THE REACH REGULATION (EC)NO:1907/2006 FORMERLY KNOWN AS DIRECTIVE 2002/61/EC)

< = Less Than
 N= Not Detected
 Requirement= 30 ppm
 ppm(part per million)= mg/ kg



Test Method	Result	Requirements
Primary Aromatic Amines EN 71 Part 9&10&11		
1- Composite sample of black, green, orange water colours (without extraction)		<30 ppm
2- Composite sample of red, white,pink water colours (without extraction)		
3- Composite sample of blue, yellow water colours (without extraction)		
<u>FORBIDDEN AMINE</u>	<u>CAS NO</u>	<u>1</u> <u>2</u> <u>3</u>
Benzidine	92-67-1	<5 <5 <5
2-naphthylamine	92-87-5	<5 <5 <5
4-chloroaniline	95-69-2	<5 <5 <5
3,3'-dichlorobenzidine	91-59-8	<5 <5 <5
3,3'-dimethoxybenzidine	97-56-3	<5 <5 <5
3,3'-dimethylbenzidine	99-55-8	<5 <5 <5
O-toluidine	106-47-8	<5 <5 <5
2-methoxyaniline (o-anisidine)	615-05-4	<5 <5 <5
Aniline	101-77-9	<5 <5 <5

< = Less Than
N= Not Detected
Requirement= 30 ppm
ppm(part per million)= mg/ kg
Detection Limit 5 ppm

**Intertek Test Hizmetleri A.S.***Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna-34197 /İSTANBUL*

Phone : +90 212 496 46 46 Fax: +90 212 452 80 55

e-mail : intertekg.turkiye@intertek.com<http://www.intertek-turkey.com>

Test Method	Result	Requirements
-------------	--------	--------------



END OF TEST REPORT